

ScandMet S SSP713 HG0

DESCRIPTION

ScandMet S is a bright silver metallised printing paper, that has been coated with a print receptive acrylic lacquer.

The material offers top print quality by all conventional print methods, like flexography, letterpress, offset and screen.

Note that special inks for non-absorbent materials should be used.

The values indicated in this leaflet are not intended to be a specification but a guide to the values that may generally be expected.

Customers should independently determine, prior to use, the suitability of any material for a specific purpose. All information is subject to change without notice.

<b>FACESTOCK</b> ScandMet S is a bright silver metallised printing paper, that has been coated with a print receptive acrylic lacquer. The material offers top print quality by all conventional print methods, like flexography, letterpress, offset and screen. Note that special inks for non-absorbent materials should be used.		
Type Paper		
PROPERTIES	METHOD	VALUE
Basis Weight	ISO 536	74 ± 3g/m²
Caliper	ISO 534	73 ± 5µ
Smoothness	ISO 5627	> 12900s
<b>REGULATORY APPROVAL</b> FSC No  *Please contact your sales representative for details		

<b>ADHESIVE</b> SSP713 has excellent initial tack and adhesion on a wide variety of substrates, including apolar, slightly rough and curved substrates. Particularly good adhesion to cardboard, plastic and glass. Note: Not advised for labelling highly plasticised materials, eg: flexible PVC		
<b>Type</b> Permanent	<b>Composition</b> Rubber	<b>Min. Application Temperature</b> 8 F
<b>Min. Service Temperature</b> -10 F	<b>Max. Application Temperature</b> 70 F	
<b>PROPERTIES</b>	<b>VALUE</b>	
<b>Stainless Steel</b>	18N	
<b>REGULATORY APPROVAL</b>		
<b>Direct Food</b>	<b>Indirect Food</b>	<b>Food contact</b>

Yes	Yes	Complies with FDA175.105, BfR XIV.
FDA 21 CFR 175.105, BfR XIV	ISEGA approved for direct contact with dry and moist non-fatty foods	
Yes	Yes	

\*Please contact your sales representative for details

## LINER

HG0 honey glassine backing allows high speed conversion and consistent dispensing on a wide range of equipment.

DESCRIPTION	METHOD	VALUE
<b>Basis Weight</b>	ISO 536	55 ± 3g/m <sup>2</sup>
<b>Caliper</b>	ISO 534	49 ± 3μ
<b>Transparency</b>	ISO 2469	50%

\*Please contact your sales representative for details

## FINAL PRODUCT

DESCRIPTION	VALUE
<b>Typical Caliper</b>	142 ± 10μ

**Format**  
Roll

**Material Shelf Life**  
12 months stored at 20°C/50% RH

\*Please contact your sales representative for details

Last update: 05/01/2024

ADDRESS:  
Beontag  
Pål Anders väg 4, 263 35  
Höganäs, Sweden  
+46 42 25 00 50  
[orders.scandstick@beontag.com](mailto:orders.scandstick@beontag.com)