



Pressure-sensitive adhesives

Acrylic

Paper

SOLAR YELLOW LABEL / TM-55 @ .8 CWT. / 40# SCK L-30

ITEM #78222

FACESTOCK A 50# yellow uncoated litho was designed with smudge resistance for high speed converting while still having excellent perforating, punching and fanfolding characteristics. This facestock is 30% PCW and will accept most standard ink methods including laser printing.	
Type Paper	
Tensile MD 36 Lbs/in	Tensile CD 13 Lbs/in
Tear MD 40 Grams	Tear CD 46 Grams
PROPERTIES	VALUE
Basis Weight	50 # Rm 25 x 38
Caliper	4.10 Mil
Opacity	90
REGULATORY APPROVAL	
Prop65 Yes	FSC No
*Please contact your sales representative for details	

ADHESIVE A specialty microsphere repositionable acrylic adhesive designed for roll to roll applications. This adhesive removes cleanly from most papers and a wide variety of substrates. Due to it\'s unique nature, TM55 cannot be coupled with any face/liner combination to achieve guaranteed lay flat properties.		
Type Removable	Composition Acrylic	Shear 0
Min. Application Temperature 40 F	Min. Service Temperature -10 F	Max. Application Temperature 150 F
PROPERTIES	VALUE	
Stainless Steel	0.2 lbs/linear in.	
Glass	0,3lbs/linear in.	
Polyethylene	0	
Corrugated	0.01 lbs./in.	
Painted Metal	0.2 lbs/linear in.	

REGULATORY APPROVAL**RoHS**
Yes**Prop65**
Yes**REACH**
Yes**TPCH**
Yes**CPSIA**
Yes**Direct Food**
No**Indirect Food**
Yes

*Please contact your sales representative for details

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type
17777**Tensile MD**
34**Tensile CD**
22**Tear MD**
32**Tear CD**
34**DESCRIPTION****VALUE****Basis Weight**

40

Caliper

2.5

REGULATORY APPROVAL**RoHS**
Yes**Prop65**
Yes**REACH**
Yes**TPCH**
Yes**CPSIA**
Yes**UL**
No**Direct Food**
No

*Please contact your sales representative for details

Last update: 08/21/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com