

Pressure-sensitive adhesives

Acrylic

Acrylic

Pape

# SOLAR YELLOW LABEL / TM-55 / MPG / 40# SCK L-30

## ITEM #78332

## **FACESTOCK**

A 50# yellow uncoated litho was designed with smudge resistance for high speed converting while still having excellent perforating, punching and fanfolding characteristics. This facestock is 30% PCW and will accept most standard ink methods including laser printing.

Type

Paper

Tensile MDTensile CD36 Lbs/in13 Lbs/inTear MDTear CD40 Grams46 Grams

PROPERTIES VALUE

**Basis Weight** 50 # Rm 25 x 38

Caliper 4.10 Mil

Opacity 90

REGULATORY APPROVAL

Prop65FSCYesNo

## **ADHESIVE**

A specialty microsphere repositionable acrylic adhesive designed for roll to roll applications. This adhesive removes cleanly from most papers and a wide variety of substrates. Due to it\'s unique nature, TM55 cannot be coupled with any face/liner combination to achieve guaranteed lay flat properties.

TypeCompositionMin. Application TemperatureRemovableAcrylic40 F

Min. Service Temperature Max. Application Temperature

-10 F 150 F

PROPERTIES

VALUE

Stainless Steel

0.2 lbs/linear in.

Glass

0.3

Polyethylene

0

Corrugated

0.01 lbs./in.

Painted Metal

0.2 lbs/linear in.

<sup>\*</sup>Please contact your sales representative for details

#### **REGULATORY APPROVAL**

**RoHS** Prop65 **REACH** No Yes Yes **CPSIA TPCH** UL Yes Yes No

**Direct Food Indirect Food** 

No Yes

## **ADHESIVE**

Туре

A specialty microsphere repositionable acrylic adhesive designed for roll to roll applications. This adhesive removes cleanly from most papers and a wide variety of substrates. Due to it\'s unique nature, TM55 cannot be coupled with any face/liner combination to achieve guaranteed lay flat properties.

Removable	Acrylic
PROPERTIES	VALUE

**Glass** 0.3 lbs/linear in.

**Polyethylene** 0

## **REGULATORY APPROVAL**

**RoHS** Prop65 **REACH** Yes Yes Yes

**TPCH CPSIA Direct Food** 

Composition

Yes Yes No

## **Indirect Food**

Yes

# **LINER**

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Ту	ре	•
17	77	7

**Tensile MD Tensile CD** 22 34

**Tear MD Tear CD** 32 34

DESCRIPTION	VALUE
Basis Weight	40
Caliper	2.5

<sup>\*</sup>Please contact your sales representative for details

<sup>\*</sup>Please contact your sales representative for details

## **REGULATORY APPROVAL**

RoHSProp65REACHYesYesYes

TPCHCPSIAULYesYesNo

#### **Direct Food**

No

\*Please contact your sales representative for details

Last update: 08/19/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 800-358-4448 orders.us@beontag.com