

TECHNI-GLOSS II HIGH GLOSS / AT333 @ 1.30 Cwt. / 40#SCK L-3

ITEM #89937

| | | |
|--|-------------------------------|---------------------|
| FACESTOCK A premium cast coated C1S white high gloss paper with a smooth print surface that offers excellent receptivity and print characteristics. The 90% gloss rating provides for the desired wet look label graphics that product manufacturers desire to enhance sales activity. | | |
| Type Paper | | |
| Tensile MD 25 Lbs/in | Tensile CD 0 Lbs/in | |
| Tear MD 35 Grams | Tear CD 40 Grams | |
| PROPERTIES | | |
| Basis Weight | 57 # Rm 24 x 26 | |
| Caliper | 3.70 Mil | |
| Opacity | 90 | |
| Brightness | 87 | |
| REGULATORY APPROVAL | | |
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | UL No |
| FSC No | | |
| *Please contact your sales representative for details | | |

| | | |
|---|--|--|
| ADHESIVE An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps. | | |
| Type Permanent | Composition Acrylic | Shear 60 |
| Min. Application Temperature -20 F | Min. Service Temperature -65 F | Max. Application Temperature 160 F |
| PROPERTIES | VALUE | |
| Stainless Steel | 4.7 lbs/linear in. | |
| Glass | 1,3lbs/linear in. | |

| | | |
|---|-------------------------|--------------------------|
| Polyethylene | 2.2 | |
| Corrugated | 1.40 lbs./in. | |
| Painted Metal | 4.4 lbs/linear in. | |
| Loop Tack | 2.20 oz/in ² | |
| REGULATORY APPROVAL | | |
| RoHS Yes | Prop65 No | REACH Yes |
| TPCH Yes | CPSIA Yes | Direct Food No |
| Indirect Food Yes | | |
| *Please contact your sales representative for details | | |

| | | |
|---|-------------------------|---------------------|
| LINER | | |
| Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing. | | |
| Type 5517342 | | |
| Tensile MD 34 | Tensile CD 22 | |
| Tear MD 32 | Tear CD 34 | |
| DESCRIPTION | | |
| VALUE | | |
| Basis Weight | 40 | |
| Caliper | 2.5 | |
| REGULATORY APPROVAL | | |
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | UL No |
| Direct Food No | | |
| *Please contact your sales representative for details | | |

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag

6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com