



Pressure-sensitive adhesives

Acrylic

Paper

TECHNI-GLOSS II HIGH GLOSS / TS585WS @ 1.6 Cwt. / 44#PK L-4

ITEM #86573

FACESTOCK A premium cast coated C1S white high gloss paper with a smooth print surface that offers excellent receptivity and print characteristics. The 90% gloss rating provides for the desired wet look label graphics that product manufacturers desire to enhance sales activity.		
Type Paper		
Tensile MD 25 Lbs/in	Tensile CD 0 Lbs/in	
Tear MD 35 Grams	Tear CD 40 Grams	
PROPERTIES		
Basis Weight	57 # Rm 24 x 26	
Caliper	3.70 Mil	
Opacity	90	
Brightness	87	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
FSC No		
*Please contact your sales representative for details		

ADHESIVE A specialty adhesive designed to adhere to slightly wet surfaces with good ultimate adhesion when applied at temperatures as low as -20 F. Excellent permanency at room temperatures. Good plasticizer, UV & solvent resistance. Excellent adhesive for hard to label substrates.		
Type Permanent	Composition Acrylic	Shear 65
Min. Application Temperature -20 F	Min. Service Temperature -65 F	Max. Application Temperature 140 F
PROPERTIES	VALUE	
Stainless Steel	4.8 lbs/linear in.	
Glass	3,2lbs/linear in.	

Polyethylene	6,5lbs/linear in.	
Corrugated	1.45 lbs./in.	
Painted Metal	4.4 lbs/linear in.	
Loop Tack	2.70 oz/in ²	
REGULATORY APPROVAL		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		
*Please contact your sales representative for details		

LINER		
A medium weight natural kraft coated 1 side (C1S) with a gloss polyethylene. Silicone coating has been added on the gloss side (C1S) for a controlled release. It has superb smoothness, excellent dimensional stability and exceptional layflat characteristics.		
Type 17745		
Tensile MD 35	Tensile CD 13	
Tear MD 35	Tear CD 50	
DESCRIPTION	VALUE	
Basis Weight	44	
Caliper	3.2	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike

Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com