

Pressure-sensitive adhesives

Acrylic

# TECHNI-GLOSS II / TS523 / MPG @ 1.5 Cwt. / 40#SCK L-10

## ITEM #996612

## **FACESTOCK**

A premium cast coated C1S white high gloss paper with a smooth print surface that offers excellent receptivity and print characteristics. The 90% gloss rating provides for the desired wet look label graphics that product manufacturers desire to enhance sales activity.

Type

Paper

**Tensile MD Tensile CD** 25 Lbs/in 0 Lbs/in Tear MD Tear CD 35 Grams 40 Grams

**PROPERTIES VALUE** 

57 # Rm 24 x 26 **Basis Weight** 

Caliper 3.70 Mil

**Opacity** 90 87

**Brightness** 

# **REGULATORY APPROVAL**

Prop65 REACH **RoHS** Yes Yes Yes **TPCH CPSIA** UL Yes No Yes

**FSC** No

# **ADHESIVE**

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent, and occasional water and oil resistance.

<b>Type</b> Permanent	<b>Composition</b> Acrylic
PROPERTIES	VALUE
Glass	2.8 lbs/linear in.
Polyethylene	1.9

<sup>\*</sup>Please contact your sales representative for details

#### **REGULATORY APPROVAL**

RoHSProp65REACHYesNoYes

TPCH CPSIA Direct Food

Yes Yes No

**Indirect Food** 

Yes

\*Please contact your sales representative for details

#### **LINER**

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

**Type** 17142

 Tensile MD
 Tensile CD

 34 Lbs/ln
 22 Lbs/ln

 Tear MD
 Tear CD

32 Grams 34 Grams

**DESCRIPTION** VALUE

Basis Weight 40 Lbs/Rm

Caliper 2.5 Mil

## **REGULATORY APPROVAL**

 RoHS
 Prop65
 REACH

 Yes
 Yes
 Yes

 TPCH
 CPSIA
 UL

 Yes
 No
 No

**Direct Food** 

No

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS: Beontag

6206 Wolf Creek Pike Trotwood, OH 45426

800-358-4448

orders.us@beontag.com