

TECHNI-THERM III / TR1 @ 1.0 Cwt. / 40#SCK L-3

ITEM #792132

FACESTOCK A coated one side thermal transfer facestock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This facestock also offers a 90% brightness and an 82% opacity.		
Type Paper		
Tensile MD 25 Lbs/in	Tensile CD 16 Lbs/in	
Tear MD 34 Grams	Tear CD 36 Grams	
PROPERTIES	VALUE	
Basis Weight	44lbs/3300 sq ft	
Caliper	2.65 Mil	
Opacity	8.2	
Brightness	90	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
FSC No		
*Please contact your sales representative for details		

ADHESIVE A specialty acrylic adhesive designed for clean removability from plastics and painted metal. Not recommended for curved or textured surfaces.		
Type Removable	Composition Acrylic	Shear 35
Min. Application Temperature 40 F	Min. Service Temperature -65 F	Max. Application Temperature 120 F
PROPERTIES	VALUE	
Stainless Steel	1.8 lbs/linear in.	
Glass	0lbs/linear in.	

Corrugated	0.55 lbs./in.	
Painted Metal	1.3 lbs/linear in.	
Loop Tack	1.35 oz/in ²	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		
*Please contact your sales representative for details		

LINER

A super calendared kraft paper which has been silicone coated one side to give a controlled release. This paper has a hard, smooth caliper for a consistent surface. Due to it's high internal strength, it will withstand all conventional processing operations including: die-cutting, butt cutting, line scoring, and dispersing.

Type

5517342

Tensile MD

30 Lbs/In

Tensile CD

20 Lbs/In

Tear MD

32 Grams

Tear CD

34 Grams

DESCRIPTION

VALUE

Basis Weight

40.5 Lbs/Rm

Caliper

2.5 Mil

REGULATORY APPROVAL

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)

