

TECHNI-THERM SP / AP151 @ 1.3 Cwt. OPAQUE / 40#SCK L-3

ITEM #73031

| | | |
|--|--------------------------------|---------------------|
| FACESTOCK A coated one side thermal transfer facestock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This facestock also offers an 86% brightness and an 87% opacity. | | |
| Type Paper | | |
| Tensile MD 26 Lbs/in | Tensile CD 18 Lbs/in | |
| Tear MD 42 Grams | Tear CD 42 Grams | |
| | | |
| PROPERTIES | VALUE | |
| Basis Weight | 42 # Rm 24 x 26 | |
| Caliper | 2.70 Mil | |
| Opacity | 87 | |
| Brightness | 86 | |
| | | |
| REGULATORY APPROVAL | | |
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | UL No |
| FSC No | | |
| *Please contact your sales representative for details | | |

| | | |
|--|--|--|
| ADHESIVE An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits. | | |
| Type Permanent | Composition Latex | Shear 80 |
| Min. Application Temperature 35 F | Min. Service Temperature -65 F | Max. Application Temperature 220 F |
| PROPERTIES | VALUE | |
| Stainless Steel | 7.3 lbs/linear in. | |
| Glass | 5.7 lbs/linear in. | |

| | | |
|---|-------------------------|--------------------------|
| Polyethylene | 6.5 | |
| Corrugated | 2.50 lbs./in. | |
| Painted Metal | 7.0 lbs/linear in. | |
| Loop Tack | 5.00 oz/in ² | |
| REGULATORY APPROVAL | | |
| RoHS Yes | Prop65 No | REACH Yes |
| TPCH Yes | CPSIA Yes | Direct Food No |
| Indirect Food Yes | | |
| *Please contact your sales representative for details | | |

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD

34

Tear MD

32

Tensile CD

22

Tear CD

34

DESCRIPTION

VALUE

Basis Weight

40

Caliper

2.5

REGULATORY APPROVAL

RoHS

Yes

TPCH

Yes

Direct Food

No

Prop65

Yes

CPSIA

Yes

REACH

Yes

UL

No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
 Beontag
 6206 Wolf Creek Pike

Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com