



Pressure-sensitive adhesives

Latex

Paper

TECHNIGLOSS II 57# AP151 65#FBK

ITEM #89944

| | | |
|--|-------------------------------|---------------------|
| FACESTOCK A premium cast coated C1S white high gloss paper with a smooth print surface that offers excellent receptivity and print characteristics. The 90% gloss rating provides for the desired wet look label graphics that product manufacturers desire to enhance sales activity. | | |
| Type Paper | | |
| Tensile MD 25 Lbs/in | Tensile CD 0 Lbs/in | |
| Tear MD 35 Grams | Tear CD 40 Grams | |
| PROPERTIES | | |
| Basis Weight | 57 # Rm 24 x 26 | |
| Caliper | 3.70 Mil | |
| Opacity | 90 | |
| Brightness | 87 | |
| REGULATORY APPROVAL | | |
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | UL No |
| FSC No | | |
| *Please contact your sales representative for details | | |

| | | |
|--|--|--|
| ADHESIVE An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits. | | |
| Type Permanent | Composition Latex | Shear 80 |
| Min. Application Temperature 35 F | Min. Service Temperature -65 F | Max. Application Temperature 220 F |
| PROPERTIES | VALUE | |
| Stainless Steel | 7.3 lbs/linear in. | |
| Glass | 5.7 lbs/linear in. | |

| | | |
|---|-------------------------|--------------------------|
| Polyethylene | 6.5 | |
| Corrugated | 2.50 lbs./in. | |
| Painted Metal | 7.0 lbs/linear in. | |
| Loop Tack | 5.00 oz/in ² | |
| REGULATORY APPROVAL | | |
| RoHS Yes | Prop65 No | REACH Yes |
| TPCH Yes | CPSIA Yes | Direct Food No |
| Indirect Food Yes | | |
| *Please contact your sales representative for details | | |

| | | |
|--|--------------------------------|---------------------|
| LINER | | |
| Fully Bleached Kraft (FBK) liner which has been silicone coated one side to give a controlled release. It is designed to withstand all die-cutting, marginal punching, perforating, fanfolding and refolding processes. It is an excellent lay-flat liner. | | |
| Type 47365 | | |
| Tensile MD 33 Lbs/In | Tensile CD 18 Lbs/In | |
| Tear MD 60 Grams | Tear CD 60 Grams | |
| DESCRIPTION | | |
| VALUE | | |
| Basis Weight | 63 Lbs/Rm | |
| Caliper | 3.8 | |
| REGULATORY APPROVAL | | |
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | UL No |
| Direct Food No | | |
| *Please contact your sales representative for details | | |

Last update: 08/19/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:
Beontag
6206 Wolf Creek Pike

Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com