

Pressure-sensitive adhesives

Acrylic

Film

TYVEK / AT333 HCWT / 50#SCK L-3

ITEM #4776

FACESTOCK

A durable sheet that is stronger than paper, less expensive and more versatile than fabrics. It is made from high density polyethylene fibers and is considered a spunbonded olefin offering a balance of physical characteristics likened to a paper, film and cloth.

Type

Film

Tensile MD Tensile CD 42 Lbs/in 48 Lbs/in **Tear MD Tear CD** 453 Grams 453 Grams **Elong MD Elong CD** 20 24

PROPERTIES VALUE

8.00 Mil Caliper

REGULATORY APPROVAL

RoHS Prop65 **REACH** Yes Yes Yes **CPSIA FSC TPCH** Yes No Yes

ADHESIVE

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

Type Composition Shear Permanent Acrylic 60

Min. Application Temperature Min. Service Temperature Max. Application Temperature

-20 F -65 F 160 F

PROPERTIES VALUE

Stainless Steel 4.9 lbs/linear in. 1.3 lbs/linear in.

2.2 **Polyethylene**

Corrugated 1.50 lbs./in.

4.7 lbs/linear in. **Painted Metal**

Loop Tack

Glass

^{*}Please contact your sales representative for details

2.40 oz/in²

REGULATORY APPROVAL

RoHSProp65REACHYesNoYes

TPCH CPSIA Direct Food

Yes Yes No

Indirect Food

Yes

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Туре

5517353

Caliper

Tensile MD Tensile CD

40 24

 Tear MD
 Tear CD

 44
 48

DESCRIPTION	VALUE
Basis Weight	50

REGULATORY APPROVAL

 RoHS
 Prop65
 REACH

 Yes
 Yes
 Yes

 TPCH
 CPSIA
 UL

 Yes
 No
 No

3.2

Direct Food

No

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 800-358-4448

orders.us@beontag.com

^{*}Please contact your sales representative for details

^{*}Please contact your sales representative for details