

Not a Current Stock Product

Please contact our team for assistance.

- Pressure-sensitive adhesives
- Rubber

SSF 933

ADHESIVE SSF933 has excellent initial tack and adhesion on a wide variety of substrates, including apolar, slightly rough and curved substrates. SSF933 is specially designed for use at low temperature and freezer conditions. For applications on cardboard in temperatures warmer than 0 °C we recommend the SSP 50N or the SSP 713.		
Type Permanent	Composition Rubber	Min. Application Temperature -20 F
Min. Service Temperature -40 F	Max. Application Temperature 50 F	
PROPERTIES	VALUE	
Stainless Steel	5,5N	
REGULATORY APPROVAL Food contact Meets composition requirement of indirect food additives regulation FDA 21-CRF 175.105		
*Please contact your sales representative for details		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com