

## Not a Current Stock Product

Please contact our team for assistance.

Pressure-sensitive adhesives Acrylic

# Techni-Therm Direct NTC / AT333 / 40#SCK L-1

#### **FACESTOCK**

A medium sensitivity, non-topcoated direct thermal label facestock designed for short-duration applications in dry environments. This paper has an initial activation temperature of 185°F and an effective activation temperature of 280°F. This product contains BPS which is known to the state of California to cause cancer, birth defects, or other reproductive harm (Prop 65).

Туре
Paper

**Tensile CD Tensile MD** >21 11.5 lbs.in

**PROPERTIES VALUE** 

**Basis Weight** 47 lbs/rm

Caliper 3.03 mil

## **REGULATORY APPROVAL**

**RoHS** Prop65 **REACH** Yes Yes No **TPCH CPSIA** UL Yes Yes No

2.2

**FSC** No

### **ADHESIVE**

**Polyethylene** 

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

Type Permanent	<b>Composition</b> Acrylic	Shear 55
Min. Application Temperature -20 F	<b>Min. Service Temperature</b> -65 F	<b>Max. Application Temperature</b> 160 F
PROPERTIES	VALUE	
Stainless Steel	4.5 lbs/linear in.	
Glass	1.3 lbs/linear in.	

<sup>\*</sup>Please contact your sales representative for details

Corrugated 1.35 lbs./in.

Painted Metal 4.2 lbs/linear in.

**Loop Tack** 2.15 oz/in<sup>2</sup>

**REGULATORY APPROVAL** 

RoHSProp65REACHYesNoYes

TPCH CPSIA Direct Food

Yes Yes No

**Indirect Food** 

Yes

\*Please contact your sales representative for details

### **LINER**

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

**Type** 11111

Tensile MD

**Tensile CD** 

34 22

 Tear MD
 Tear CD

 32
 34

Basis Weight 40

Caliper 2.5

**REGULATORY APPROVAL** 

 RoHS
 Prop65
 REACH

 Yes
 Yes
 Yes

 TPCH
 CPSIA
 UL

 Yes
 No
 No

**Direct Food** 

No

\*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 800-358-4448

orders.us@beontag.com