## Not a Current Stock Product

Please contact our team for assistance.

Pressure-sensitive adhesives Acrylic

Acrylic

Paper

# Techni-Therm SP / TP170 / LPG @ 1.40 Cwt. / TP160 @ 1.40 Cwt. / 40#SCK L-10 / 50#SCK L-10

A coated one side thermal transfer facestock with outstanding ink receptivity and print characteristics. It also offers good flexibilit and high internal strength for ease in converting. This facestock also offers an 86% brightness and an 87% opacity.			
<b>Type</b> Paper			
<b>Tensile MD</b> 26 Lbs/in	<b>Tensile CD</b> 18 Lbs/in		
<b>Tear MD</b> 42 Grams	Tear CD 42 Grams		
PROPERTIES	VALUE		
Basis Weight	42 # Rm 24 x 26		
Caliper	2.70 Mil		
Opacity	87		
Brightness	86		
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA	UL	
Yes	Yes	No	
<b>fsc</b> No			

## ADHESIVE

A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

**Type** Permanent **Composition** Acrylic

**Min. Application Temperature** 35 F **Min. Service Temperature** -65 F **Shear** 300

**Max. Application Temperature** 180 F

PROPERTIES	VALUE
Stainless Steel	5.2 lbs/linear in.
Glass	3,2lbs/linear in.
Polyethylene	1.6
Corrugated	1.40 lbs./in.
Painted Metal	5.2 lbs/linear in.
Loop Tack	2.20 oz/in <sup>2</sup>

## REGULATORY APPROVAL

<b>RoHS</b>	<b>Ргор65</b>	<b>REACH</b>
Yes	No	Yes
<b>TPCH</b>	<b>CPSIA</b>	<b>Direct Food</b>
Yes	Yes	Yes
Indirect Food		

Yes

\*Please contact your sales representative for details

## ADHESIVE

An improved general purpose acrylic adhesive showing good initial tack, shear and high ultimate adhesion. It has a good plasticizer, UV and solvent resistance. This adhesive also displays excellent die-cutting and stripping traits & has excellent adhesion to many different substrates, with an application temperature of +25 F.

<b>Type</b> Permanent <b>Min. Application Temperature</b> 25 F	<b>Composition</b> Acrylic <b>Min. Service Temperature</b> -65 F	<b>Shear</b> 80 <b>Max. Application Temperature</b> 200 F
PROPERTIES	VALUE	
Stainless Steel	6.9 lbs/linear in.	
Glass	0lbs/linear in.	
Polyethylene	2.3	
Corrugated	1.25 lbs./in.	
Painted Metal	6.5 lbs/linear in.	
Loop Tack	3.00 oz/in <sup>2</sup>	
REGULATORY APPROVAL		
RoHS	Prop65	REACH
Yes	Yes	Yes
<b>трсн</b> Yes	<b>CPSIA</b> Yes	<b>Direct Food</b> No
Indirect Food Yes		
*Please contact your sales representa	tive for details	

#### LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

<b>Туре</b> 17142			
Tensile MD	Tensile CD		
34	22		
Tear MD	Tear CD		
32	34		
DESCRIPTION	VALUE		
Basis Weight	40		
Caliper	2.5		
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA	UL	
Yes	Yes	No	
<b>Direct Food</b> No			
*Please contact your sales repres	sentative for details		

### LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Tensile MD	Tensile CD		
43	27		
Tear MD	Tear CD		
44	48		
DESCRIPTION	VALUE		
Basis Weight	50		
Caliper	3,2		
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA		
Yes	Yes		
*Please contact your sales repre	asentative for details		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG's standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS: Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 <u>800-358-4448</u> <u>orders.us@beontag.com</u>