



Pressure-sensitive adhesives

Acrylic

Paper

17" X 22" CHARTREUSE FLUORESCENT / PERMANENT / 80# SCOREBACK L-3

ITEM #SC-021

Facestock

A premium coated one side face stock in a bright fluorescent color with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting.

Type

Paper

Tensile MD

26 Lbs/in

Tensile CD

14 Lbs/in

Tear MD

45 Grams

Tear CD

53 Grams

Properties

Value

Caliper

3.80 Mil

Opacity

0

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

*Please contact your sales representative for details

Adhesive

A general purpose acrylic adhesive showing good initial tack with high shear and ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Composition

Acrylic

Type

Permanent

Shear

300

Application Temperature

35 F

Min. Application Temperature

-65 F

Max. Application Temperature

180 F

Properties

Value

Stainless Steel

5.2 lbs/linear in.

| | |
|----------------------|---------------------------|
| Glass | 2.8 |
| Polyethylene | 2.9 |
| Corrugated | 1.40 lbs./in. |
| Painted Metal | 5.2 lbs/linear in. |
| Loop Tack | 2.20 lbs./in ² |

Regulatory Approval

| | | |
|---------------------------|-----------------------------|---------------------|
| RoHS Yes | Prop65 No | REACH Yes |
| TPCH Yes | CPSIA Yes | UL No |
| Direct Food Yes | Indirect Food Yes | |

*Please contact your sales representative for details

Liner

This liner is clay-coated bleached kraft designed for roll-to-sheet applications. It is manufactured with scores every 1.25" apart.

Type
9019084

| | |
|--------------------------------|--------------------------------|
| Tensile MD 36 Lbs/In | Tensile CD 21 Lbs/In |
| Tear MD 61 Grams | Tear CD 71 Grams |

| Description | Value |
|---------------------|-----------|
| Basis Weight | 72 Lbs/Rm |
| Caliper | 4.6 Mil |

Regulatory Approval

| | | |
|--------------------------|----------------------|---------------------|
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | UL No |
| Direct Food No | | |

*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com