

# FSC ScandCoat MC SSP 713 K2



ITEM #F120002H0N000

## Description

ScandCoat MC is a medium gloss machine coated paper with good whiteness. It is a versatile paper which is suitable for a very wide range of primary label work.

Developed for general colour printing, ScandCoat MC gives good colour lift and can be printed by flexography, rotary or flat-bed letterpress, offset lithography, screen process and can be foil blocked and varnished.

It can also be thermal transfer overprinted with suitable smudge resistant ribbons.

The values indicated in this leaflet are not intended to be a specification but a guide to the values that may generally be expected. Customers should independently determine, prior to use, the suitability of any material for a specific purpose. All information is subject to change without notice.

### Facestock

ScandCoat MC is a medium gloss machine coated paper with good whiteness. It is a versatile paper which is suitable for a very wide range of primary label work. Developed for general color printing, ScandCoat MC gives good color lift and can be printed by flexography, rotary or flat-bed letterpress, offset lithography, screen process and can be foil blocked and varnished. It can also be thermal transfer overprinted with suitable smudge resistant ribbons.

### Type

Paper

### Properties

### Value

### Caliper

2.7 Mil

### Regulatory Approval

#### RoHS

Yes

#### Prop65

Yes

#### REACH

Yes

#### TPCH

Yes

#### CPSIA

Yes

#### UL

No

#### FSC

Yes

\*Please contact your sales representative for details

### Adhesive

SSP713 has excellent initial tack and adhesion on a wide variety of substrates, including apolar, slightly rough and curved substrates. Particularly good adhesion to cardboard, plastic and glass. Note: Not advised for labelling highly plasticised materials, eg: flexible PVC

<b>Composition</b> Rubber	<b>Type</b> Permanent	<b>Application Temperature</b> 8 F
<b>Min. Application Temperature</b> -10 F	<b>Max. Application Temperature</b> 70 F	

### Typical Adhesion values

Properties	Value
<b>Stainless Steel</b>	18N

### Regulatory Approval

<b>Food contact</b> Complies with FDA175.105, BfR XIV.	<b>FDA 21 CFR 175.105, BfR XIV</b> Yes	<b>ISEGA approved for direct contact with dry and moist non-fatty foods</b> Yes
---	---	--

\*Please contact your sales representative for details

### Liner

ScandSil Kraft 66 (K2) is a bleached kraft backing with good lay-flat properties and dimensional stability.

**Type**  
Paper

Description	Method	Value
<b>Basis Weight</b>	ISO 536	66 ± 3g/m <sup>2</sup>
<b>Caliper</b>	ISO 534	69 ± 4μ

\*Please contact your sales representative for details

### Final product

ScandCoat MC is a medium gloss machine coated paper with good whiteness. It is a versatile paper which is suitable for a very wide range of primary label work.

Developed for general colour printing, ScandCoat MC gives good colour lift and can be printed by flexography, rotary or flat-bed letterpress, offset lithography, screen process and can be foil blocked and varnished.

It can also be thermal transfer overprinted with suitable smudge resistant ribbons.

The values indicated in this leaflet are not intended to be a specification but a guide to the values that may generally be expected. Customers should independently determine, prior to use, the suitability of any material for a specific purpose. All information is subject to change without notice.

**Format**  
Roll

Description	Value
<b>Typical Caliper</b>	146 ± 10μ

## **Regulatory Approval**

### **Certificate**

The product is registered to SCS-COC-004802 FSC™ Mix credit.

### **Material Shelf Life**

12 months stored at 20°C/50% RH

\*Please contact your sales representative for details

Last update: 05/01/2024

ADDRESS:

Beontag

Pål Anders väg 4, 263 35

Höganäs, Sweden

[orders.scandstick@beontag.com](mailto:orders.scandstick@beontag.com)