

## Not a Current Stock Product

Please contact our team for assistance.

Self adhesives

Latex

Latex

Film

1 Mil Polyester TC Clear / AP151 Opaque @ 1.50 Cwt. / AP151 / LPG @ 1.30 Cwt. / 1.5 Mil Clear Polyester L-3 / 1.5 MIL CLEAR PET LINER L-3C

### FACESTOCK

This facestock displays high clarity and good UV resistance. The versatile topcoating is compatible with solvent base, water based and UV curable inks and can also perform well when used in silk screen or offset print processes.

#### Type

Film

#### Tensile MD

28000 Psi

#### Tensile CD

34000 Psi

#### Elong MD

300

#### Elong CD

110

#### PROPERTIES

#### VALUE

#### Caliper

1.00 Mil

#### REGULATORY APPROVAL

#### RoHS

Yes

#### Prop65

Yes

#### REACH

Yes

#### TPCH

Yes

#### CPSIA

Yes

#### UL

No

#### FSC

No

### ADHESIVE

An outstanding general purpose permanent opaque adhesive that has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting and stripping traits. Provides opacity for cover up applications.

#### Type

Permanent

#### Shear

0

#### Min. Application Temperature

35°C

#### Min. Service Temperature

-64°C

#### Max. Service Temperature

220°C

#### PROPERTIES

#### VALUE

#### Stainless Steel

7.3 lbs/linear in.

#### Typical Peel Adhesion

5,7 lbs/linear in.

<b>Polyethylene</b>	6.5
<b>Painted Metal</b>	7.0 lbs/linear in.

**REGULATORY APPROVAL**

<b>RoHS</b> Yes	<b>Prop65</b> No	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>Direct Food</b> No
<b>Indirect Food</b> Yes		

**ADHESIVE**

An outstanding general purpose permanent adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing & can be used on many different substrates. Displays excellent die-cutting & stripping traits.

<b>Type</b> Permanent	<b>Shear</b> 80	<b>Min. Application Temperature</b> 35°C
<b>Min. Service Temperature</b> -65°C	<b>Max. Service Temperature</b> 220°C	

**PROPERTIES VALUE**

<b>Stainless Steel</b>	7.3 lbs/linear in.
<b>Typical Peel Adhesion</b>	5,7 lbs/linear in.
<b>Polyethylene</b>	6.5
<b>Corrugated</b>	2.50 lbs./in.
<b>Painted Metal</b>	7.0 lbs/linear in.
<b>Loop Tack</b>	5.00 oz/in <sup>2</sup>

**REGULATORY APPROVAL**

<b>RoHS</b> Yes	<b>Prop65</b> No	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>Direct Food</b> No
<b>Indirect Food</b> Yes		

**BACKING**

A 1.5 mil polyester liner which has been silicone coated one side to give a controlled release. It has extremely high internal strength for ease in manufacturing, converting and end-usage, making it an outstanding liner for high speed, automatic applications.

<b>Tensile MD</b> 33000	<b>Tensile CD</b> 0
<b>Tear MD</b> 0	<b>Tear CD</b> 0

**DESCRIPTION VALUE**

<b>Basis Weight</b>	0		
<b>Caliper</b>	1,5		
<b>REGULATORY APPROVAL</b>			
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes	
<b>TPCH</b> Yes	<b>CPSIA</b> Yes		

<b>BACKING</b>			
A 1.5 Mil clear pet liner which is silicone coated one side to give a controlled release. Uniform caliper and high internal strength enhance the excellent die-cutting characteristics of this liner.			
<b>Type</b> 17617			
<b>Tensile MD</b> 32000	<b>Tensile CD</b> 0		
<b>Tear MD</b> 0	<b>Tear CD</b> 0		
<b>DESCRIPTION</b>		<b>VALUE</b>	
<b>Caliper</b>		1.5	
<b>REGULATORY APPROVAL</b>			
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes	
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No	
<b>Direct Food</b> No			

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:

Beontag  
Pål Anders väg 4, 263 35  
Höganäs, Sweden  
+46 42 25 00 50

[orders.scandstick@beontag.com](mailto:orders.scandstick@beontag.com)