

Not a Current Stock Product

Please contact our team for assistance.

- Self adhesives
- Latex
- Latex
- Film

1.2 mil Iridescent Film / AP151 LIGHT GRAY OPAQUE / AP151 Opaque @ 1.50 Cwt. / 1.5 MIL CLEAR PET LINER L-50X / 1.5 MIL CLEAR PET LINER L-3C

FACESTOCK An optical layer film composed of a polyester/acrylic optical core with a copolyester skin layer. It's generally used in laminations to paper and plastics for such end uses as gift wrap, greeting cards, packaging cartons, labels & etc.	
Type Film	
Tensile MD 9500 Psi	Tensile CD 9100 Psi
PROPERTIES	VALUE
Caliper	1.20 Mil
REGULATORY APPROVAL	
Prop65 Yes	FSC No

ADHESIVE An outstanding general purpose permanent opaque adhesive that has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing & can be used on many different substrates. Displays excellent die cutting & stripping traits. PMS 421 light gray opaque color.		
Type Permanent	Shear 80	Min. Application Temperature 35°C
Min. Service Temperature -65°C	Max. Service Temperature 220°C	
PROPERTIES	VALUE	
Stainless Steel	7.3 lbs/linear in.	
Typical Peel Adhesion	5.7 lbs/linear in.	
Polyethylene	6.5	
Corrugated	2.50 lbs./in.	
Painted Metal	7.0 lbs/linear in.	
Loop Tack	5.00 oz/in²	

REGULATORY APPROVAL**RoHS**
Yes**Prop65**
No**REACH**
Yes**TPCH**
Yes**CPSIA**
Yes**Direct Food**
Yes**Indirect Food**
Yes**ADHESIVE**

An outstanding general purpose permanent opaque adhesive that has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting and stripping traits. Provides opacity for cover up applications.

Type
Permanent**Shear**
0**Min. Application Temperature**
35°C**Min. Service Temperature**
-64°C**Max. Service Temperature**
220°C**PROPERTIES****VALUE****Stainless Steel**

7.3 lbs/linear in.

Typical Peel Adhesion

5,7 lbs/linear in.

Polyethylene

6.5

Painted Metal

7.0 lbs/linear in.

REGULATORY APPROVAL**RoHS**
Yes**Prop65**
No**REACH**
Yes**TPCH**
Yes**CPSIA**
Yes**Direct Food**
No**Indirect Food**
Yes

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:

Beontag
Pål Anders väg 4, 263 35
Höganäs, Sweden
+46 42 25 00 50

orders.scandstick@beontag.com