

Not a Current Stock Product

Please contact our team for assistance.

- Self adhesives
- Acrylic
- Film

2 Mil Gloss White TC Polyester / AT333 / 1.2 MIL PET

FACESTOCK A 2 mil white TC polyester with a smooth gloss finish. This film has excellent durability and resistance to harsh weather and environments including extreme temperatures, chemicals, moisture, solvents and UV light. Compatible with water-based flexo, UV flexo and thermal transfer print methods.		
Type Film		
Tensile MD 28000 Psi	Tensile CD 34000 Psi	
Tear MD 1500 Grams		
Elong MD 300	Elong CD 110	
PROPERTIES	VALUE	
Caliper	2.00 Mil	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	FSC No

ADHESIVE An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.		
Type Permanent	Shear 55	Min. Application Temperature -20°C
Min. Service Temperature -65°C	Max. Service Temperature 160°C	
PROPERTIES	VALUE	
Stainless Steel	4.5 lbs/linear in.	
Typical Peel Adhesion	1.3 lbs/linear in.	
Polyethylene	2.2	
Corrugated		

1.35 lbs./in.

Painted Metal

4.2 lbs/linear in.

Loop Tack

2.15 oz/in²

REGULATORY APPROVAL

RoHS

Yes

Prop65

No

REACH

Yes

TPCH

Yes

CPSIA

Yes

Direct Food

No

Indirect Food

Yes

BACKING

An economical 1.2 mil clear polyester film liner good for an array of prime label applications.

Type

716666

Tensile MD

30000

Tensile CD

0

Tear MD

0

Tear CD

0

DESCRIPTION

VALUE

Caliper

1.2

REGULATORY APPROVAL

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:

Beontag

Pål Anders väg 4, 263 35

Höganäs, Sweden

+46 42 25 00 50

orders.scandstick@beontag.com