

# Not a Current Stock Product

Please contact our team for assistance.

- Self adhesives
- Acrylic
- Film

## 3.2 mil White DT TC BOPP / ALL TEMP / 2.5 mil SCK L-3

<b>FACESTOCK</b>		
Facestock(3.2 mil White DT TC BOPP): A white direct thermal topcoated, biaxially oriented (BOPP) film that may be used in a wide variety of pressure sensitive label applications. The solid white polypropylene core is treated one side with a print receptive gloss coating for superb ink adhesion, and has great stiffness for efficient dispensability.		
<b>Type</b> Film		
<b>Tensile MD</b> 11500 psi	<b>Tensile CD</b> 28000 psi	
<b>Elong MD</b> 179	<b>Elong CD</b> 43	
<b>PROPERTIES</b>		
<b>VALUE</b>		
<b>Caliper</b>	3.2 mil	
<b>REGULATORY APPROVAL</b>		
<b>RoHS</b> Yes	<b>Prop65</b> No	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>FSC</b> No		

<b>ADHESIVE</b>		
An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Excellent permanency at room temperatures. Very good plasticizer, UV and solvent resistance. This adhesive offers a neutral ph level (Acid Free)		
<b>Type</b> Permanent	<b>Shear</b> 100	<b>Min. Application Temperature</b> -20°C
<b>Min. Service Temperature</b> -65°C	<b>Max. Service Temperature</b> 160°C	
<b>PROPERTIES</b>	<b>VALUE</b>	
<b>Stainless Steel</b>	5.1 lbs/linear in.	
<b>Typical Peel Adhesion</b>	4,4 lbs/linear in.	
<b>Polyethylene</b>	4.2	
<b>Corrugated</b>		

1.50 lbs./in.

**Painted Metal**

4.9 lbs/linear in.

**Loop Tack**

2.90 oz/in<sup>2</sup>

**REGULATORY APPROVAL**

**RoHS**

Yes

**Prop65**

Yes

**REACH**

Yes

**TPCH**

Yes

**CPSIA**

Yes

**Direct Food**

Yes

**Indirect Food**

Yes

**BACKING**

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a hard smooth caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

**Type**

18360

**Tensile MD**

35

**Tensile CD**

16

**Tear MD**

42

**Tear CD**

46

**DESCRIPTION**

**VALUE**

**Basis Weight**

40

**Caliper**

2.5

**REGULATORY APPROVAL**

**RoHS**

Yes

**Prop65**

Yes

**REACH**

Yes

**TPCH**

Yes

**CPSIA**

Yes

**UL**

No

**Direct Food**

No

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

**ADDRESS:**

Beontag

Pål Anders väg 4, 263 35

Höganäs, Sweden

+46 42 25 00 50

[orders.scandstick@beontag.com](mailto:orders.scandstick@beontag.com)