

Not a Current Stock Product

Please contact our team for assistance.

- Self adhesives
- Latex
- Paper

38# Techni-Therm / AP151 / 40#SCK L-3

FACESTOCK A lightweight grade thermal transfer paper that offers a smooth surface for good bar code reproduction. It also offers good smudge resistance and high strength for fast matrix stripping. This lower basis weight will improve yield.		
Type Paper		
Tensile CD 17 lb/in		
Tear MD 42		
PROPERTIES		VALUE
Basis Weight		38#
Caliper		2.8
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	FSC No

ADHESIVE An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.		
Type Permanent	Shear 80	Min. Application Temperature 35°C
Min. Service Temperature -65°C	Max. Service Temperature 220°C	
PROPERTIES	VALUE	
Stainless Steel	7.3 lbs/linear in.	
Typical Peel Adhesion	5.7 lbs/linear in.	
Polyethylene	6.5	
Corrugated	2.50 lbs./in.	

7.0 lbs/linear in.

Loop Tack

5.00 oz/in²

REGULATORY APPROVAL

RoHS
Yes

Prop65
No

REACH
Yes

TPCH
Yes

CPSIA
Yes

Direct Food
Yes

Indirect Food
Yes

BACKING

A super calendared kraft paper which has been silicone coated one side to give a controlled release. This paper has a hard, smooth caliper for a consistent surface. Due to it's high internal strength, it will withstand all conventional processing operations including: die-cutting, butt cutting, line scoring, and dispersing.

Type
5517342

Tensile MD
30 Lbs/In

Tensile CD
20 Lbs/In

Tear MD
32 Grams

Tear CD
34 Grams

DESCRIPTION

VALUE

Basis Weight

40.5 Lbs/Rm

Caliper

2.5 Mil

REGULATORY APPROVAL

RoHS
Yes

Prop65
Yes

REACH
Yes

TPCH
Yes

CPSIA
Yes

UL
No

Direct Food
No

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.
BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:
Beontag
Pål Anders väg 4, 263 35
Höganäs, Sweden
+46 42 25 00 50
orders.scandstick@beontag.com