

## Not a Current Stock Product

Please contact our team for assistance.

Self adhesives

Acrylic Paper

# 55# Semigloss / AT150 / 40#SCK L-3

#### **FACESTOCK**

A calendar coated one side semigloss stock with excellent ink receptivity and print characteristics. This stock offers an 88% brightness and opacity and a 70% gloss rating.

Туре

Paper

**Tensile CD** 

16 lb/in

Tear MD

51 g

**PROPERTIES VALUE** 

**Basis Weight** 55 lb/3300sf

Caliper 2.9 mil

**REGULATORY APPROVAL** 

**RoHS** Prop65 **REACH** Yes Yes Yes **CPSIA TPCH** UL No Yes Yes

**FSC** No

### **ADHESIVE**

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT150 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps

Shear Min. Application Temperature -20°C Permanent 105

Min. Service Temperature Max. Service Temperature

160°C -65°C

**PROPERTIES VALUE Stainless Steel** 5.4 lbs/linear in. **Typical Peel Adhesion** 4.4 lbs/linear in. Polyethylene 4.2

Corrugated 1.50 lbs./in.

Painted Metal 5.2 lbs/linear in.

Loop Tack 3.00 oz/in<sup>2</sup>

**REGULATORY APPROVAL** 

RoHSProp65REACHYesYesYes

TPCH CPSIA Direct Food

Yes Yes Yes

**Indirect Food** 

Yes

#### **BACKING**

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

**Type** 5517342

Tensile MD Tensile CD

34 22

Tear MD Tear CD 32 34

**DESCRIPTION** VALUE

Basis Weight 40

Caliper 2.5

**REGULATORY APPROVAL** 

 RoHS
 Prop65
 REACH

 Yes
 Yes
 Yes

 TPCH
 CPSIA
 UL

 Yes
 No
 No

**Direct Food** 

No

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:

Beontag Pål Anders väg 4, 263 35 Höganäs, Sweden +46 42 25 00 50

orders.scandstick@beontag.com