

Not a Current Stock Product

Please contact our team for assistance.

Self adhesives Rubber Paper

7 mil C1S TT Tag / TL250 @ 1.7 Cwt.

FACESTOCK			
Туре			
Paper			
Tensile MD	Tensile CD		
60 Lbs/in	32 Lbs/in		
Tear MD	Tear CD		
150 Grams	160 Grams		
PROPERTIES	VALUE		
Basis Weight	119lbs/3300 sq ft		
Caliper	6.90 Mil		
Brightness	88		
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA	FSC	
Yes	Yes	No	

ADHESIVE

An outstanding general purpose permanent adhesive which has high initial tack and high ultimate adhesion. It is used for tire label and many other difficult to label substrates.

Type

Yes

TPCH

Permanent

PROPERTIES	VALUE		
Typical Peel Adhesion	6.7 lbs/linear in.		
Polyethylene	7,5		
REGULATORY APPROVAL			
RoHS	Prop65	REACH	

Yes

UL

No

CPSIA

Yes Yes No

Direct Food Indirect Food Yes

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:

Beontag Pål Anders väg 4, 263 35 Höganäs, Sweden +46 42 25 00 50

orders.scandstick@beontag.com