#### Self adhesives

Hot Mel<u>t</u>

#### SSP 50N Paper

# FSC ScandCoat MC SSP 50N WG0



## FACESTOCK

ScandCoat MC is a medium gloss machine coated paper with good whiteness. It is a versatile paper which is suitable for a very wide range of primary label work. Developed for general colour printing, ScandCoat MC gives good colour lift and can be printed by flexography, rotary or flat-bed letterpress, offset lithography, screen process and can be foil blocked and varnished. It can also be thermal transfer overprinted with suitable smudge resistant ribbons.

#### Туре

Paper

PROPERTIES	METHOD	VALUE
Basis Weight	ISO 536	78 ± 3g/m²
Caliper	ISO 534	68 ± 5µ
Opacity	ISO 2471	89%
Brightness	ISO 11475	120%
Smoothness	ISO 8791-4 - (PPS 10, WS)	0,9µ

#### **REGULATORY APPROVAL**

FSC Yes

## ADHESIVE

ScandStick Permanent 50N has excellent initial tack with high bond strength at elevated, room and chilled temperatures, as well as in moist conditions. It has been formulated to adhere to a wide variety of substrates, including corrugated cardboard, low surface energy materials like polyethylene and non-polar surfaces. SSP 50N provides enhanced conversion characteristics, allowing die-cutting at higher speeds and is designed for both paper and synthetic face materials. Limitation: Not suitable for labelling plasticised PVC.

General purpose chill permanent

<b>Type</b> Permanent <b>Max. Service Temperature</b> 70°C	<b>Min. Application Temperature</b> -5°C	<b>Min. Service Temperature</b> -40°C
PROPERTIES	METHOD	VALUE
Peel	FTM 1 (20 min)	19N
Tack	FTM 9	18N

Indirect Food Yes

ISEGA approved for direct contact with dry and moist non-fatty foods Yes

## BACKING

WG0 White glassine backing allows high speed conversion and consistent dispensing on a wide range of equipment

Туре	
D	

Paper

DESCRIPTION	METHOD	VALUE
Basis Weight	ISO 536	$60 \pm 3 g/m^2$
Caliper	ISO 534	53 ± 3µ
Transparency	ISO 2469	49%

#### **FINAL PRODUCT**

DESCRIPTION	VALUE
Typical Caliper	129 ± 10µ

# Format

Roll

# Certificate

The product is registered to SAI-COC-010567 FSC <sup>™</sup> Mix credit.

#### Regulations

Food Packaging Applications: The adhesive raw materials are listed under European/US food packaging regulations (BgVV XIV or FDA 21 175.105) and are safe for use in limited contact with foodstuffs. Toy and Packaging Regulations: The materials used have been tested and comply with the current heavy metals regulations EN71-3 Safety of Toys and the UK Packaging (Essential Requirements) Regulations 1998.

### **Material Shelf Life**

12 months stored at 20°C/50% RH

**sku** F120001J0N000

Replaces all previous information.

Last update: 01/05/2024

1. All information, recommendations and descriptions of our Products are based on research, tests and data believed to be reliable and as such they must be considered as a guide and not as a guarantee nor a warranty. 2. Tests must be conducted by the customer to determine suitability of the products for their purposes and/or ambient, in any application and condition. 3. This document is valid only as information and can be revised without notice. For values and other technical product specifications, contact our Sales or Technical Department.

ADDRESS:

Beontag Pål Anders väg 4, 263 35 Höganäs, Sweden +46 42 25 00 50 <u>orders.scandstick@beontag.com</u>