

# FSC ScandCoat MC SSP 713 K2



## DESCRIPTION

The values indicated in this leaflet are not intended to be a specification but a guide to the values that may generally be expected. Customers should independently determine, prior to use, the suitability of any material for a specific purpose. All information is subject to change without notice.

### FACESTOCK

ScandCoat MC is a medium gloss machine coated paper with good whiteness. It is a versatile paper which is suitable for a very wide range of primary label work. Developed for general colour printing, ScandCoat MC gives good colour lift and can be printed by flexography, rotary or flat-bed letterpress, offset lithography, screen process and can be foil blocked and varnished. It can also be thermal transfer overprinted with suitable smudge resistant ribbons.

**Type**  
Paper

PROPERTIES	METHOD	VALUE
<b>Basis Weight</b>	ISO 536	78 ± 3g/m <sup>2</sup>
<b>Caliper</b>	ISO 534	68 ± 5µ
<b>Opacity</b>	ISO 2471	89%
<b>Brightness</b>	ISO 11475	120%
<b>Smoothness</b>	ISO 8791-4 - (PPS 10, WS)	0,9µ

### REGULATORY APPROVAL

**FSC**  
Yes

### BACKING

ScandSil Kraft 66 (K2) is a bleached kraft backing with good lay-flat properties and dimensional stability.

**Type**  
Paper

DESCRIPTION	METHOD	VALUE
<b>Basis Weight</b>	ISO 536	66 ± 3g/m <sup>2</sup>
<b>Caliper</b>	ISO 534	69 ± 4µ

### FINAL PRODUCT

DESCRIPTION	VALUE
Typical Caliper	146 ± 10μ
<div><div>Format</div><div>Roll</div><div>Certificate</div><div>The product is registered to SCS-COC-004802 FSC™ Mix credit.</div><div>Material Shelf Life</div><div>12 months stored at 20°C/50% RH</div><div>SKU</div><div>F120002H0N000</div></div>	

Last update: 01/05/2024

ADDRESS:  
Beontag  
Pål Anders väg 4, 263 35  
Höganäs, Sweden  
+46 42 25 00 50  
[orders.scandstick@beontag.com](mailto:orders.scandstick@beontag.com)