Self adhesives

Hot Melt

SSP 50N Paper

# FSC Scandtherm TCS SSP 50N 22g HG0



## FACESTOCK

ScandTherm TCS is a protected direct chemi-thermal label, which is a woodfree paper with a coating of thermosensitive dyes which turn black when heated. There is a top coating which protects the label surface and thermally printed images from above, against contaminants such as moisture, oil, grease and plasticisers from films. ScandTherm TCS can be printed by water based and UV inks and varnishes designed for use with direct thermal papers. This thermal paper has a standard sensitivity making it suitable for print speeds up to 200-250mm per second depending on printer settings. It is recommended that customers assess both the pre-print and the overprint characteristics under end use conditions before proceeding to long runs.

<b>Type</b> Paper <b>Top Coating</b> Yes		
Image color	Printing speed (Max.)	
Black	200 mm/s	
Didek	200 1111,0	
PROPERTIES	METHOD	VALUE
Basis Weight	ISO 536	75 ± 5g/m²
Caliper	ISO 534	80 ± 8µ
calipol		ου - ομ
REGULATORY APPROVAL		
FSC		
Yes		

## ADHESIVE

ScandStick Permanent 50N has excellent initial tack with high bond strength at elevated, room and chilled temperatures, as well as in moist conditions. It has been formulated to adhere to a wide variety of substrates, including corrugated cardboard, low surface energy materials like polyethylene and non-polar surfaces. SSP 50N provides enhanced conversion characteristics, allowing die-cutting at higher speeds and is designed for both paper and synthetic face materials. Limitation: Not suitable for labelling plasticised PVC.

General purpose chill permanent

<b>Type</b> Permanent <b>Max. Service Temperature</b> 70°C	Min. Application Temperature -5°C	Min. Service Temperature -40°C
<b>REGULATORY APPROVAL</b> <b>Direct Food</b> Yes	<b>Indirect Food</b> Yes	<b>Food contact</b> Meets composition requirement of indirect food additives regula- tion FDA175.105, BfR XIV.

## BACKING

HG0 honey glassine backing allows high speed conversion and consistent dispensing on a wide range of equipment.

# Туре

Paper

DESCRIPTION	METHOD	VALUE
Caliper	ISO 534	49 ± 3µ
Transparency	ISO 2469	50%

	<b>\L P</b> F		ICT
<b>FIIN</b>		ίυυι	וטנ

DESCRIPTION	VALUE
Typical Caliper	140 ± 14µ

# Format

Roll

### Certificate

The product is registered to SAI-COC-010567 FSC <sup>™</sup> Mix credit.

## Regulations

Food Packaging Applications: The adhesive raw materials are listed under European/US food packaging regulations (BgVV XIV or FDA 21 175.105) and are safe for use in limited contact with foodstuffs. Toy and Packaging Regulations: The materials used have been tested and comply with the current heavy metals regulations EN71-3 Safety of Toys and the UK Packaging (Essential Requirements) Regulations 1998.

### **Material Shelf Life**

12 months stored at 20°C/50% RH

**SKU** F300000J0N200

Replaces all previous information.

#### Last update: 01/05/2024

1. All information, recommendations and descriptions of our Products are based on research, tests and data believed to be reliable and as such they must be considered as a guide and not as a guarantee nor a warranty. 2. Tests must be conducted by the customer to determine suitability of the products for their purposes and/or ambient, in any application and condition. 3. This document is valid only as information and can be revised without notice. For values and other technical product specifications, contact our Sales or Technical Department.

ADDRESS: Beontag Pål Anders väg 4, 263 35 Höganäs, Sweden +46 42 25 00 50 <u>orders.scandstick@beontag.com</u>