

Self adhesives

Hot Melt

SSP 90

Film

ScandFilm PP60 W TC SSP 90 28g HG0

FACESTOCK

ScandFilm PP60 W TC is a super white opaque polypropylene film with a proprietary cavitated core giving high yield and excellent opacity. It is topcoated with a new versitaile printable coating. ScandFilm PP60 W TC has a fine balance of flexibility and rigidity to suit most general label dispensing and application requirements. ScandFilm PP60 W TC G is also a durable material with a very high resistance to moisture and many chemicals. ScandFilm PP60 W TC is designed for use in pressure sensitive labelling where superior appearance and graphics are desired. Excellent UV printability. ScandFilm PP60 W TC is not recommended for fan folding..

Type

Film

Top Coating

Yes

PROPERTIES	METHOD	VALUE
Basis Weight	ISO 536	45,4 ± 3g/m ²
Caliper	ISO 534	60 ± 3µ
Gloss	ASTM-D2457 (45°)	63%

ADHESIVE

SSP 90 is a very aggressive adhesive, specially designed for use on difficult and rough surfaces. Typical use is - tyre labelling. - The increased coat-weight could have a negative effect on conversion speed and adhesive set-off on diecutting - tools.

Heavy duty speciality permanent

TypeMin. Application TemperatureMin. Service TemperaturePermanent 5° C -20° C

Max. Service Temperature

70°C

REGULATORY APPROVAL

ISEGA approved for direct contact with dry and moist non-fatty foods

No

BACKING

HG0 honey glassine backing allows high speed conversion and consistent dispensing on a wide range of equipment.

Туре

Paper

DESCRIPTION ME	IETHOD	VALUE
Caliper	SO 534	49 ± 3µ
Transparency	SO 2469	50%

FINAL PRODUCT	
DESCRIPTION	VALUE
Typical Caliper	123 ± 12µ

Format

Roll

Regulations

Food Packaging Applications: The adhesive raw materials are listed under European/US food packaging regulations (BgVV XIV or FDA 21 175.105) and are safe for use in limited contact with foodstuffs. Toy and Packaging Regulations: The materials used have been tested and comply with the current heavy metals regulations EN71-3 Safety of Toys and the UK Packaging (Essential Requirements) Regulations 1998.

Material Shelf Life

12 months stored at 20°C/50% RH

SKU

128195P0N800

Replaces all previous information.

Last update: 01/05/2024

1. All information, recommendations and descriptions of our Products are based on research, tests and data believed to be reliable and as such they must be considered as a guide and not as a guarantee nor a warranty. 2. Tests must be conducted by the customer to determine suitability of the products for their purposes and/or ambient, in any application and condition. 3. This document is valid only as information and can be revised without notice. For values and other technical product specifications, contact our Sales or Technical Department

ADDRESS:

Beontag Pål Anders väg 4, 263 35 Höganäs, Sweden +46 42 25 00 50

orders.scandstick@beontag.com