

Not a Current Stock Product

Please contact our team for assistance.

- Self adhesives
- Acrylic
- Paper

Techni-Therm Direct II WS / TS583 @ 2.10 Cwt. / 2.5 Mil White Glassine TC-1C

FACESTOCK A top coated direct thermal facestock designed for grocery weigh scale label applications where water, oil and heat resistance is essential. This 3.1mil thickness paper also resists plasticizers at room temperature and images best at 8 IPS.		
Type Paper		
Tear MD 53 Grams	Tear CD 55 Grams	
PROPERTIES		
Basis Weight	52	
Caliper	3.10 Mil	
Brightness	77	
REGULATORY APPROVAL		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	FSC No

ADHESIVE A specialty adhesive designed to adhere to hard to label surfaces with excellent ultimate adhesion when applied at temperatures as low as -20 F. Outstanding permanency at room temperatures. This adhesive has good plasticizer, UV & solvent resistance and high initial tack.		
Type Permanent	Shear 70	Min. Application Temperature -20°C
Min. Service Temperature -65°C	Max. Service Temperature 160°C	
PROPERTIES	VALUE	
Stainless Steel	5.9 lbs/linear in.	
Typical Peel Adhesion	4,2lbs/linear in.	
Polyethylene	6,5lbs/linear in.	
Corrugated	1.50 lbs./in.	

Painted Metal	5.1 lbs/linear in.
Loop Tack	3.20 oz/in ²
REGULATORY APPROVAL	
RoHS Yes	Prop65 No
TPCH Yes	CPSIA Yes
Indirect Food Yes	REACH Yes
	Direct Food No

BACKING	
A white semi-transparent and smooth caliper liner that has been silicone coated one side to give a controlled release.	
Type 19019	
Tensile MD 28	Tensile CD 19
Tear MD 27	Tear CD 27
DESCRIPTION	VALUE
Basis Weight	35
Caliper	2.5
REGULATORY APPROVAL	
RoHS Yes	Prop65 Yes
TPCH Yes	CPSIA Yes
Direct Food No	REACH Yes
	UL No

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:
Beontag
Pål Anders väg 4, 263 35
Höganäs, Sweden
+46 42 25 00 50
orders.scandstick@beontag.com