

Not a Current Stock Product

Please contact our team for assistance.

- Self adhesives
- Acrylic
- Paper

Techni-Therm Direct RX / AT150 / 1.7 Mil Glassine L-3

FACESTOCK An exceptional topcoated thermal label facestock specifically engineered for pharmacy prescription vial labels where superior image durability is required. The brightness of this Direct Thermal product is designed for dark images on pharmacy thermal printers.		
Type Paper		
Tear MD 50 Grams	Tear CD 83 Grams	
PROPERTIES		
Basis Weight	53	
Caliper	3.20 Mil	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	FSC No

ADHESIVE An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT150 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps		
Type Permanent	Shear 105	Min. Application Temperature -20°C
Min. Service Temperature -65°C	Max. Service Temperature 160°C	
PROPERTIES	VALUE	
Stainless Steel	5.4 lbs/linear in.	
Typical Peel Adhesion	4.4 lbs/linear in.	
Polyethylene	4.2	
Corrugated	1.50 lbs./in.	
Painted Metal	5.2 lbs/linear in.	

Loop Tack		3.00 oz/in ²
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food Yes
Indirect Food Yes		

BACKING		
A white semi-transparent and smooth caliper liner that has been silicone coated one side to give a controlled release.		
Type 901905		
Tensile MD 39800	Tensile CD 15900	
Tear MD 28	Tear CD 30	
DESCRIPTION		
Basis Weight	41	
Caliper	1.7	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:
Beontag
Pål Anders väg 4, 263 35
Höganäs, Sweden
+46 42 25 00 50
orders.scandstick@beontag.com