

Not a Current Stock Product

Please contact our team for assistance.

- Self adhesives
- Acrylic
- Acrylic
- Paper

Techni-Therm SP / TP170 / LPG @ 1.40 Cwt. / TP160 @ 1.40 Cwt. / 40#SCK L-10 / 50#SCK L-10

FACESTOCK		
A coated one side thermal transfer facestock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This facestock also offers an 86% brightness and an 87% opacity.		
Type Paper		
Tensile MD 26 Lbs/in	Tensile CD 18 Lbs/in	
Tear MD 42 Grams	Tear CD 42 Grams	
PROPERTIES	VALUE	
Basis Weight	42 # Rm 24 x 26	
Caliper	2.70 Mil	
Opacity	87	
Brightness	86	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
FSC No		

ADHESIVE		
A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.		
Type	Shear	Min. Application Temperature
Permanent	300	35°C
Min. Service Temperature	Max. Service Temperature	
-65°C	180°C	
PROPERTIES	VALUE	

Stainless Steel	5.2 lbs/linear in.	
Typical Peel Adhesion	3,2lbs/linear in.	
Polyethylene	1.6	
Corrugated	1.40 lbs./in.	
Painted Metal	5.2 lbs/linear in.	
Loop Tack	2.20 oz/in ²	
REGULATORY APPROVAL		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food Yes
Indirect Food Yes		

ADHESIVE		
An improved general purpose acrylic adhesive showing good initial tack, shear and high ultimate adhesion. It has a good plasticizer, UV and solvent resistance. This adhesive also displays excellent die-cutting and stripping traits & has excellent adhesion to many different substrates, with an application temperature of +25 F.		
Type Permanent	Shear 80	Min. Application Temperature 25°C
Min. Service Temperature -65°C	Max. Service Temperature 200°C	
PROPERTIES	VALUE	
Stainless Steel	6.9 lbs/linear in.	
Typical Peel Adhesion	0lbs/linear in.	
Polyethylene	2.3	
Corrugated	1.25 lbs./in.	
Painted Metal	6.5 lbs/linear in.	
Loop Tack	3.00 oz/in ²	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		

BACKING
Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type 17142		
Tensile MD 34	Tensile CD 22	
Tear MD 32	Tear CD 34	
DESCRIPTION		
VALUE		
Basis Weight	40	
Caliper	2.5	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		

BACKING		
Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
Tensile MD 43	Tensile CD 27	
Tear MD 44	Tear CD 48	
DESCRIPTION	VALUE	
Basis Weight	50	
Caliper	3,2	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:
Beontag
Pål Anders väg 4, 263 35

Höganäs, Sweden

+46 42 25 00 50

orders.scandstick@beontag.com