

## Not a Current Stock Product

Please contact our team for assistance.

Self adhesives

Acrylic

## TP160 @ 1.50 Cwt. / TP160 @ 1.50 Cwt.

## **ADHESIVE**

An improved general purpose acrylic adhesive showing good initial tack, shear and high ultimate adhesion. It has a good plasticizer, UV and solvent resistance. This adhesive also displays excellent die-cutting and stripping traits & has excellent adhesion to many different substrates, with an application temperature of +25 F.

Type Shear Min. Application Temperature

Permanent 80 25°C

Min. Service Temperature Max. Service Temperature

-65°C 200°C

PROPERTIES VALUE

**Stainless Steel** 7.0 lbs/linear in.

**Typical Peel Adhesion** 5,3lbs/linear in.

Polyethylene 6.5

Corrugated 1.25 lbs./in.

Painted Metal 6.6 lbs/linear in.

Loop Tack 3.00 oz/in<sup>2</sup>

**REGULATORY APPROVAL** 

RoHSProp65REACHYesYesYes

TPCH CPSIA Direct Food

Yes Yes No

**Indirect Food** 

Yes

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:

Beontag Pål Anders väg 4, 263 35 Höganäs, Sweden +46 42 25 00 50

orders.scandstick@beontag.com