

Not a Current Stock Product

Please contact our team for assistance.

Self adhesives

Acrylic

TS523 @ .90 Cwt.

ADHESIVE

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

Type Permanent	Shear 110	Min. Application Temperature 35°C
Min. Service Temperature -65°C	Max. Service Temperature 180°C	

PROPERTIES

VALUE

Stainless Steel	4.7 lbs/linear in.
Typical Peel Adhesion	2,8lbs/linear in.
Polyethylene	2.9
Corrugated	1.20 lbs./in.
Painted Metal	4.2 lbs/linear in.
Loop Tack	1.70 oz/in ²

REGULATORY APPROVAL

RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:

Beontag
Pål Anders väg 4, 263 35
Höganäs, Sweden
+46 42 25 00 50

orders.scandstick@beontag.com