

Not a Current Stock Product

Please contact our team for assistance.

- Autoadhesivo
- Acrylic
- Film

2.6 mil Pearl White BOPP / TS523 @ 1.70 Cwt. / 50#SCK L-3

FRONTAL	
A top coated white cavitated BOPP face stock with excellent stability and die cutting capabilities. Printability includes water, solvent, and UV based inks on flexo, gravure, UV letterpress and rotary screen printing systems. It is also thermal transfer printable. This film has excellent stiffness, gloss, and opacity.	
Tipo Film	
Tensile MD 11360 Psi	Tensile CD 22580 Psi
Elong MD 140	Elong CD 47
PROPIEDADES	VALOR
Espesor	2.60 Mil
APROBACIÓN REGLAMENTARIA	
Prop65 Si	FSC No

ADHESIVO		
A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.		
Tipo Permanent	Composición Acrylic	Shear 350
PROPIEDADES	VALOR	
Stainless Steel	6.1 lbs/linear in.	
Adhesividad Vidrio	2,8lbs/linear in.	
Polyethylene	2.9	
Corrugated	1.50 lbs./in.	
Painted Metal	5.4 lbs/linear in.	
Loop Tack	2.70 oz/in²	
APROBACIÓN REGLAMENTARIA		

RoHS Si	Prop65 No	REACH Si
TPCH Si	CPSIA Si	Contacto directo con los alimentos No
Contacto indirecto con los alimentos Si		

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Tipo 5517353	
Tensile MD 40	Tensile CD 24
Tear MD 44	Tear CD 48

DESCRIPCIÓN	VALOR
Gramaje	50
Espesor	3.2

APROBACIÓN REGLAMENTARIA		
RoHS Si	Prop65 Si	REACH Si
TPCH Si	CPSIA Si	UL No
Contacto directo con los alimentos No		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.
BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

DIRECCIÓN:
Beontag
Avenida Presidente Kennedy, 2427 - Jardim Lar Parana
Campo Mourão - PR, Brasil
+55 (44) 3518-3500