

# Not a Current Stock Product

Please contact our team for assistance.

- Autoadhesivo
- Acrylic
- Film

## 4 mil Soft White Vinyl / TS523 @ 1.00 Cwt. / 8 PT Tag Liner L-3

<b>FRONTAL</b> A 4 mil flexible white vinyl with polymeric plasticizers, formulated to provide optimum performance with pressure sensitive adhesives. The top-coating provides outstanding adhesion to various printing inks.		
<b>Tipo</b> Film		
<b>Tensile MD</b> 3900	<b>Tensile CD</b> 3800	
<b>Tear MD</b> 100	<b>Tear CD</b> 100	
<b>PROPIEDADES</b>		
<b>VALOR</b>		
<b>Espesor</b>	4.0	
<b>APROBACIÓN REGLAMENTARIA</b>		
<b>RoHS</b> Si	<b>Prop65</b> Si	<b>REACH</b> Si
<b>TPCH</b> Si	<b>CPSIA</b> Si	<b>FSC</b> No

<b>ADHESIVO</b> A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.		
<b>Tipo</b> Permanent	<b>Composición</b> Acrylic	<b>Shear</b> 110
<b>PROPIEDADES</b>	<b>VALOR</b>	
<b>Stainless Steel</b>	4.7 lbs/linear in.	
<b>Adhesividad Vidrio</b>	2,8lbs/linear in.	
<b>Polyethylene</b>	2.9	
<b>Corrugated</b>	1.20 lbs./in.	
<b>Painted Metal</b>	4.2 lbs/linear in.	
<b>Loop Tack</b>	1.70 oz/in²	

<b>APROBACIÓN REGLAMENTARIA</b>		
<b>RoHS</b> Si	<b>Prop65</b> No	<b>REACH</b> Si
<b>TPCH</b> Si	<b>CPSIA</b> Si	<b>Contacto directo con los alimentos</b> No
<b>Contacto indirecto con los alimentos</b> Si		

LINER

An 8pt, 100# tag liner which has been silicone coated one side to give a controlled release. It has exceptionally high internal strength to withstand all conventional processing operations including die-cutting, perforating, fanfolding and refolding processes.

Tipo

17380

Tensile MD

63

Tensile CD

34

Tear MD

149

Tear CD

156

DESCRIPCIÓN

VALOR

Gramaje

102

Espessor

8

APROBACIÓN REGLAMENTARIA

RoHS

Si

Prop65

Si

REACH

Si

TPCH

Si

CPSIA

Si

UL

No

Contacto directo con los alimentos

No

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

DIRECCIÓN:  
Beontag  
Avenida Presidente Kennedy, 2427 - Jardim Lar Parana  
Campo Mourão - PR, Brasil  
+55 (44) 3518-3500