

# Not a Current Stock Product

Please contact our team for assistance.

- Autoadhesivo
- Latex
- Paper

7 mil C1S TT Tag / TL250 / LPG @ 2.50 Cwt.

FRONTAL		
Tipo Paper		
Tensile MD 60 Lbs/in	Tensile CD 32 Lbs/in	
Tear MD 150 Grams	Tear CD 160 Grams	
PROPIEDADES	VALOR	
Gramaje	119lbs/3300 sq ft	
Espesor	6.90 Mil	
Brightness	88	
APROBACIÓN REGLAMENTARIA		
RoHS Si	Prop65 Si	REACH Si
TPCH Si	CPSIA Si	FSC No

ADHESIVO		
An outstanding general purpose permanent adhesive which has high initial tack and high ultimate adhesion. It is used fo r tire label and many other difficult to label substrates.		
Tipo Permanent	Composición Latex	Shear 80
PROPIEDADES	VALOR	
Stainless Steel	8.3 lbs/linear in.	
Adhesividad Vidrio	6,7lbs/linear in.	
Polyethylene	7,5	
Corrugated	2.90 lbs./in.	
Painted Metal	8.0 lbs/linear in.	
Loop Tack	5.40 oz/in²	

**APROBACIÓN REGLAMENTARIA**

**RoHS**  
Si

**Prop65**  
No

**REACH**  
Si

**TPCH**  
Si

**CPSIA**  
Si

**Contacto directo con los alimentos**  
No

**Contacto indirecto con los alimentos**  
Si

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

DIRECCIÓN:  
Beontag  
Avenida Presidente Kennedy, 2427 - Jardim Lar Parana  
Campo Mourão - PR, Brasil  
+55 (44) 3518-3500