

Not a Current Stock Product

Please contact our team for assistance.

- Autoadhesivo
- Acrylic
- Film

7.5 mil White Uncoated Lumbertuff / ALL TEMP / 40#SCK L-10

FRONTAL		
A high density polyethylene film construction designed for economical applications where high tear strength and superior tear resistance is required. FDA Compliant		
Tipo Film		
Tensile MD 30 Lbs/in	Tensile CD 33 Lbs/in	
PROPIEDADES	VALOR	
Espesor	7.50 Mil	
Opacidad	70	
APROBACIÓN REGLAMENTARIA		
RoHS Si	Prop65 Si	REACH Si
TPCH Si	CPSIA Si	FSC No

ADHESIVO		
An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Excellent permanency at room temperatures. Very good plasticizer, UV and solvent resistance. This adhesive offers a neutral ph level (Acid Free)		
Tipo Permanent	Composición Acrylic	Shear 100
PROPIEDADES	VALOR	
Stainless Steel	5.1 lbs/linear in.	
Adhesividad Vidrio	4,4 lbs/linear in.	
Polyethylene	4.2	
Corrugated	1.50 lbs./in.	
Painted Metal	4.9 lbs/linear in.	
Loop Tack	2.90 oz/in²	

APROBACIÓN REGLAMENTARIA		
RoHS Si	Prop65 Si	REACH Si
TPCH Si	CPSIA Si	Contacto directo con los alimentos Si
Contacto indirecto con los alimentos Si		

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Tipo

17142

Tensile MD

34

Tensile CD

22

Tear MD

32

Tear CD

34

DESCRIPCIÓN

VALOR

Gramaje

40

Espesor

2.5

APROBACIÓN REGLAMENTARIA

RoHS

Si

Prop65

Si

REACH

Si

TPCH

Si

CPSIA

Si

UL

No

Contacto directo con los alimentos

No

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

DIRECCIÓN:
Beontag
Avenida Presidente Kennedy, 2427 - Jardim Lar Parana
Campo Mourão - PR, Brasil
+55 (44) 3518-3500