

Not a Current Stock Product

Please contact our team for assistance.

- Autoadhesivo
- Latex
- Film

ScandFilm PP60 W TC / AP151 Opaque @ 1.30 Cwt. / 1.5 MIL CLEAR PET LINER L-3C

FRONTAL <p>ScandFilm PP60 W TC is a super white opaque polypropylene film with a proprietary cavitated core giving high yield and excellent opacity. It is topcoated with a new versatile printable coating. ScandFilm PP60 W TC has a fine balance of flexibility and rigidity to suit most general label dispensing and application requirements. ScandFilm PP60 W TC G is also a durable material with a very high resistance to moisture and many chemicals. ScandFilm PP60 W TC is designed for use in pressure sensitive labelling where superior appearance and graphics are desired. Excellent UV printability. ScandFilm PP60 W TC is not recommended for fan folding.</p>		
Tipo Film		
Top Coating Si		
PROPIEDADES	MÉTODO DE PRUEBA	VALOR
Gramaje	ISO 536	45,4 ± 3g/m²
Espesor	ISO 534	60 ± 3µ
Gloss	ASTM-D2457 (45°)	63

ADHESIVO		
An outstanding general purpose permanent opaque adhesive that has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting and stripping traits. Provides opacity for cover up applications.		
Tipo Permanent	Composición Latex	Shear 80
PROPIEDADES	VALOR	
Stainless Steel	7.3 lbs/linear in.	
Adhesividad Vidrio	5,7 lbs/linear in.	
Polyethylene	6,5	
Corrugated	2.50 lbs./in.	
Painted Metal	7.0 lbs/linear in.	
Loop Tack	5.00 oz/in²	
APROBACIÓN REGLAMENTARIA		

RoHS Si	Prop65 No	REACH Si
TPCH Si	CPSIA Si	Contacto directo con los alimentos No
Contacto indirecto con los alimentos Si		

LINER

A 1.5 Mil clear pet liner which is silicone coated one side to give a controlled release. Uniform caliper and high internal strength enhance the excellent die-cutting characteristics of this liner.

Tipo 17617	
Tensile MD 32000	Tensile CD 0
Tear MD 0	Tear CD 0

DESCRIPCIÓN	VALOR
Espesor	1.5

APROBACIÓN REGLAMENTARIA

RoHS Si	Prop65 Si	REACH Si
TPCH Si	CPSIA Si	UL No
Contacto directo con los alimentos No		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

DIRECCIÓN:
Beontag
Avenida Presidente Kennedy, 2427 - Jardim Lar Parana
Campo Mourão - PR, Brasil
+55 (44) 3518-3500