

Not a Current Stock Product

Please contact our team for assistance.

- Autoadhesivo
- Acrylic
- Paper

Techni-Therm Direct NTC / TS523 / LPG @ 1.30 Cwt. / 40#SCK L-3 TU

FRONTAL		
A medium sensitivity, non-topcoated direct thermal label facestock designed for short-duration applications in dry environments. This paper has an initial activation temperature of 185°F and an effective activation temperature of 280°F. This product contains BPS which is known to the state of California to cause cancer, birth defects, or other reproductive harm (Prop 65).		
Tipo Paper		
Tensile MD >21	Tensile CD 11.5 lbs.in	
PROPIEDADES	VALOR	
Gramaje	47 lbs/rm	
Espessor	3.03 mil	
APROBACIÓN REGLAMENTARIA		
RoHS Si	Prop65 No	REACH Si
TPCH Si	CPSIA Si	UL No
FSC No		

ADHESIVO		
A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent, and occasional water and oil resistance.		
Tipo Permanent	Composición Acrylic	Shear 300
PROPIEDADES	VALOR	
Stainless Steel	5.2 lbs/linear in.	
Adhesividad Vidrio	2,8lbs/linear in.	
Polyethylene	1.9	
Corrugated	1.40 lbs./in.	
Painted Metal	5.2 lbs/linear in.	

Loop Tack 2.20 oz/in ²		
APROBACIÓN REGLAMENTARIA		
RoHS Si	Prop65 No	REACH Si
TPCH Si	CPSIA Si	Contacto directo con los alimentos No
Contacto indirecto con los alimentos Si		

LINER Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. Technicote Ultimate silicone release coating provides consistent stripping at high converting speeds through a flat release profile. This paper has a smooth, caliper consistent surface and withstands all conventional processing operations.		
Tipo 718322		
Tensile MD 30	Tensile CD 20	
Tear MD 32	Tear CD 34	
DESCRIPCIÓN		
Gramaje	40	
Espesor	2.5	
APROBACIÓN REGLAMENTARIA		
RoHS Si	Prop65 Si	REACH Si
TPCH Si	CPSIA Si	UL No
Contacto directo con los alimentos No		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

DIRECCIÓN:
Beontag
Avenida Presidente Kennedy, 2427 - Jardim Lar Parana
Campo Mourão - PR, Brasil
+55 (44) 3518-3500