

Not a Current Stock Product

Please contact our team for assistance.

- Autoadhesivo
- Acrylic
- Paper

Techni-Therm III / Permanent / 40#SCK BASE LINER

FRONTAL A coated one side thermal transfer facestock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This facestock also offers a 90% brightness and an 82% opacity.		
Tipo Paper		
Tensile MD 25 Lbs/in	Tensile CD 16 Lbs/in	
Tear MD 34 Grams	Tear CD 36 Grams	
PROPIEDADES		
Gramaje	44lbs/3300 sq ft	
Espesor	2.65 Mil	
Opacidad	8.2	
Brightness	90	
APROBACIÓN REGLAMENTARIA		
RoHS Si	Prop65 Si	REACH Si
TPCH Si	CPSIA Si	UL No
FSC No		

ADHESIVO A general purpose acrylic adhesive showing good initial tack with high shear and ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.	
Tipo Permanent	Composición Acrylic
PROPIEDADES	VALOR
Adhesividad Vidrio	2.8 lbs/linear in.
Polyethylene	1.5

APROBACIÓN REGLAMENTARIA		
RoHS Si	Prop65 Si	REACH Si
TPCH Si	CPSIA Si	Contacto directo con los alimentos Si
Contacto indirecto con los alimentos Si		

LINER

Supercalendered Kraft (SCK liner). This paper has a smooth surface with a consistent caliper. Due to its high internal strength, it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Tipo		
18840		
Tensile MD	Tensile CD	
34	22	
Tear MD	Tear CD	
32	34	

DESCRIPCIÓN	VALOR
Gramaje	40
Espessor	2.5

APROBACIÓN REGLAMENTARIA		
RoHS	Prop65	REACH
Si	Si	Si
TPCH	CPSIA	UL
Si	Si	No
Contacto directo con los alimentos		
No		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

DIRECCIÓN:
Beontag
Avenida Presidente Kennedy, 2427 - Jardim Lar Parana
Campo Mourão - PR, Brasil
+55 (44) 3518-3500